



# V.A.LATEX CO.,LTD

Properties	SKIM BLOCK	
	Specification	International Standard
Dirt Content , max ; % by weight	0.160	ISO 249
Ash Content , max ; % by weight	1.00	ASTM D1278-91a
Volatile Matter , max ; by weight	1.50	SMR Bullentin No.7
Nitrogen , max ; by weight	3.00	SMR Bullentin No.7
Initial Plasticity (PO) , min	30.00	SMR Bullentin No.7
P30 , min	10.00	SMR Bullentin No.7
Plastic Retaintion Index (PRI) , min	35.00	SMR Bullentin No.7
Mooney Viscosity ML (1' + 4') 100 °C , max	95.00	SMR Bullentin No.7
Hardness Shore A , max	45.00	-