



V.A.LATEX CO.,LTD

Properties	TMTD FREE High Ammonia	
	Specification	International Standard
Total Solid Content (TSC) , min ; %	61.50	ISO 124
Dry Rubber Content (DRC) , min ; %	60.00	ISO 126
Non rubber, max ; %	2.00	-
Ammonia content on total Weight , min ; %	0.70	ISO 125
Ammonia content on water phase, min ; %	1.80	-
Mechanical Stability Time @ 55 % TSC, max ; sec.	200 or agreed between the two parties	ISO 35
Volatile Fatty Acid Number (VFA No) ,max	0.030 or agreed between the two parties	ISO 506
pH Value	10.00-11.00	ISO 976
Potassium Hydroxide Number (KOH No.) , max	0.60 or agreed between the two parties	ISO 127
Coagulum content ,max ; %	0.0050	ISO 706
Magnesium content (ppm) on % TSC , max	35 or agreed between the two parties	ISO 11852
Viscosity at (61 % TSC,Spindle No.1,60 rpm) ;cPs	60 - 100	ISO 1652
TMTD/ZnO LEVEL ; %	NIL	-
TOTAL SOAP CONTENT ; %	NIL	-